**CHEMICAL RESISTANCE:**

| | | | |
|---|---|---|---|
| | | Test Procedure: **ASTM D1308** | |
| *Recommended | R | **Test Media** | |
| * Recommended Conditionally (washdown within 1 hour of spillage) | C | Acetone | C |
| | | Antifreeze | R |
| *Not Recommended | N | Benzene | R |
| *Suitable for immersion and/or splash and spillage conditions | 1 | Benzoic Acid | R |
| | | Butyl Alcohol | R |
| *Suitable for occasional or intermittent contact for up to 72 hours | 2 | Butyl Cellosolve | R |
| | | Carbon Dioxide | R |
| | | Calcium Hypochlorite | N |
| Test Procedure: **ASTM D3912** | | Chlorine (5000 ppm in water) | 2 |
| | | Citric Acid | R |
| **Test Media** | | Cylloexanol | R |
| Acetic Acid 10% | C | Dichloacetic Acid | C |
| Ammonium Hydroxide 10%/20 | R | Dimethyl Formamide | N |
| Diesel Fuel | R | Ethanol | 2 |
| Gasoline | R | Ethylene Glycol | 1 |
| Hydraulic Fluid | R | Gasoline | R |
| Hydrochloric Acid 5%/10% | R | Hexane | R |
| Methanol | R | Hydraulic Oil | R |
| Motor Oil | R | Lactic Acid 10% | 1 |
| MTBE | R | Methylene Chloride | C |
| MTBE/Gasoline 5% | R | Methyl Ethyl Ketone | C |
| NaCl/Water 10% | R | Methanol | R |
| Phosphoric Acid 10% | R | Mineral Spirits | R |
| Potassium Hydroxide 10%/20% | R | Monobutyl Ether | R |
| Sodium Hydroxide 10%/20%/50% | R | Nitric Acid 20% | C |
| Sugar/Water 10% | R | Phenol | 2 |
| Sulfuric Acid 5%/10% | R | Skydrol | 2 |
| Skydrol | 2 | Sodium Bicarbonate | R |
| Toluene | C | Sodium Chloride | R |
| Water | R | Sodium Hydroxide 50% | R |
| 2-Methylbutane | R | Sodium Hypochlorite 10% | 2 |
| | | Stearic Acid | R |
| | | Sulfuric Acid 70% | N |
| | | Trichloroethylene | C |
| | | Trisodium Phosphate | R |
| | | Toluene | N |
| | | Vinegar | |
| | | Xylene | N |

**Parson Environmental Products, Inc. * P.O. Box 4474 * Reading, PA 19606**
**Toll Free: (800) 356-9023 * Voice: (610) 582-6060 * Fax: (610) 582-6064**
**WEB SITE: www.parsonenvironmental.com**